

Manufacturer: FDS DRY STRIPPING TECHNOLOGY GMBH
Germany

Distributor: Emsodur AG
Industriepark Vial 2
CH-7013 Domat/Ems
Tel.: +41 81 632 80 11

Trade Mark: **DRY STRIP[®] Type 3**

Chemical characteristics: granulated aminoplastics as per ISO 2112 / DIN 7708

Particle shape: irregular with sharp, angular edges and corners

Standard sizes: ASTM E-11 / ISO 565 T2 / DIN 4787

12/16 mesh	1,70 / 1,18 mm
16/20 mesh	1,18 / 0,85 mm
20/30 mesh	0,85 / 0,60 mm
20/40 mesh	0,85 / 0,43 mm
30/40 mesh	0,60 / 0,43 mm
40/60 mesh	0,43 / 0,25 mm
60/80 mesh	0,25 / 0,18 mm

Physical characteristics:

Density: 1,4 - 1,6 g/cm³
Hardness: 64-72 Barcol, resp. 4,0 MOH
Water absorption: ≤ 10% by wt
Residual Impurities: 0,005% metallic and/or non-metallic particules

Chemical characteristics:

pH-value at 250 g/l H₂O, 20°: 4 - 8
Content of organic soluble components: max. 0,5%
Ash content: max. 2%

Resistance against

- weak acids and alkalines:	resistant
- strong acids and alkalines:	non-resistant
- organic solubles:	resistant

Thermic characteristics:

Flashpoint: non applicable
Thermic decomposition: 450° C
Lower explosion limit: 60 g/m³
Inflamability UL 94 1,6 mm: V-0

Durability of storage: unlimited, when stored in a cool and dry place

Authorizations: Meets Military Specification (USA)MIL-P-85891A

Country of origin: Germany